III. THE GROUP OF MATERIALS CONSIDERED AND ITS "MISSING MEMBERS"

The I-I-VI compounds [see Fig. 1(a)] based on two monovalent and one exavalent species form a rich group of solids that can be thought of as (formally) derived from the well-known octet [17,18] binary II-VI semiconductors with the zinc-blende structure by splitting the column II cation into two monovalent cations, either from column IA or IB of the periodic table. The zinc-blende structure, in principle, can accommodate both cations by stuf ng the extra cation in the (1/2,1/2,1/2) vacancy site [1,19–22], after the (0,0,0) and (1/4,1/4,1/4) sites along the diagonal of the cubic cell, thus obtaining the so-called lled tetrahedral structures [17] [i.e., the half-Heuseler alloy ($C1_b$) structure depicted in Fig. 2(a)].

$C1_b$ is only one of the numerous structure types in which the I-I-VI compounds can form and some of the frequently recurring structure types are depicted in Fig. 2. Most notably, while several I-I-VI compounds have been previously synthesized [check marks in Fig. 1(a)], there are numerous missing compounds that are unreported members in this group [question marks in Fig. 1(a)] as well as in several other $A^{I}B^{I}X^{VI}$ groups. We focus on the RbBX compounds (shown in the upper left corner of each square in Fig. 1) and speci cally on those with X^{VI} = S and Se, which are not reported in the ICSD [23], while RbCuO has been synthesized and found [24] in a structure analogous to that of CuLiO.

IV. HIGH-THROUGHPUT PREDICTION OF THE STRUCTURES OF RbCuS AND RbCuSe

In Ref. [1], the structures of the missing I-I-VI compounds were predicted by the procedure described in the previous section, screening 41 structure prototypes. The compounds that are predicted to be stable are summarized in Fig. 1(c). Here, we revisit (and revise) the predictions of the lowest-energy structure for RbCuS and RbCuSe by performing ab initio local total-energy minimization calculations with stricter convergence criteria (see the Supplemental Material [25] for details). We consider a subset of the 41 prototypes used in Ref. [1] (namely, a selection of the lowest-energy structures that were predicted in that work for the I-I-VI systems) as the starting trial structures and relax them to the local energy minimum. The ladder diagram of Fig. 3 shows the total energies of RbCuS and RbCuSe for the fully relaxed structures of the considered prototypes. Each level is associated to a local energy-minimum structure and is labeled after the name of the known compound whose experimental structure was used as the starting point of the local minimization. For instance, the CuLiO-type minimum is obtained substituting Rb on Li and S on the O sites in the experimental structure of CuLiO and then doing a full relaxation.

We nd that the RbAuS-type structure (see Table II) is the lowest-energy one both for RbCuS and RbCuSe. The CuLiO type is the prototype next in energy, at about 0.06 eV/f.u., from the RbAuS-type structure, followed by the MgSrSi-, LiCaN-, and ZrBeSi-type structures. MgSrSi and LiCaN have structures with the same space-group symmetry and set of Wyckoff sites, and therefore correspond to the same formal structure type. However, they have different numerical values of the Wyckoff coordinates and lattice parameters, thus exhibiting

TABLE II. Crystallographic parameters (space-group symmetry and lattice parameters) of RbCuS for the following structures: (a) the experimental structure measured by single-crystal x-ray diffraction; (b) the RbAuS-type local minimum structure obtained performing a full relaxation of RbCuS starting from the RbAuS atom positions and lattice vectors and substituting Au with Cu; and (c) the structure found by GSGO and shown in Fig. 4(c).

	Exp.	Relaxed RbAuS-type structure	GSGO
Space group (No.)	Cmcm] a8017.8(24.767.5(wnth)-5(])-47539-259.)057		

VI

reported by Boller [27]. At the best of our knowledge there

correspond to structures that might be quite different from that of the global energy minimum. Several global optimization methods are currently widely used to search for the lowest-energy structure of a solid by exploring, in an unbiased fashion, its Born-Oppenheimer surface calculated by density functional theory (DFT). These computational approaches include evolutionary algorithms [31–35], particle swarm optimization [36], and methods based on molecular dynamics, such as simulated annealing [37], minima hopping [38], and metadynamics [39]. Also, a search approach based on the local energy minimization of randomly generated structures [40] has been successfully applied to numerous materials.

Here, we apply the global space-group optimization (GSGO) [34,35] implementation of the evolutionary algorithm for crystal-structure prediction. The evolutionary search starts from a set of candidate structures generated by randomly selecting the lattice vectors and atom positions. The population of candidate structures is then evolved through a series of generations in which the higher-energy structures (e.g., 25% of the whole population) are discarded and substituted with new structures produced by the evolutionary operators of mutation and heredity, here consisting of a cut-and-splice crossover [33]. Each newly generated structure is fully relaxed to the closest local minimum of the total energy of the periodic system that is calculated by DFT. The fully relaxed structures are finally included in the next generation of the population (see, e.g., Ref. [35] for some applications). Since previous tests [1,3] of crystal-structure prediction by the two approaches of GSGO automatic search and screening of a range of formal structure types gave the same answers, the computationally more costly GSGO is not always used.

The GSGO algorithm predicts for RbCuS the structure shown in Fig. 4(c) (see the Supplemental Material [25] for the structure predicted by GSGO for RbCuSe). In order to determine the space group and set of Wyckoff positions in the GSGO structures, we used the FINDSYM [41] symmetry analysis algorithm. We find that the GSGO-predicted structures for RbCuS and RbCuSe have the $C2cm$ space-group symmetry with the lattice parameters and Wyckoff positions reported in Tables II and III and in the Supplemental Material [25], respectively, for RbCuS and RbCuSe. The GSGO predicted and the experimental structures have virtually the same total energies when these are fully relaxed by DFT and are lower in energy than the local minimum RbAuS-type structure (see Fig. 3) found by prototype screening and shown in Fig. 4(c). The Rb, Cu, and X^{VI} atoms occupy the same Wyckoff orbits in the GSGO structures as in the experimental structures, and

compounds. However, we do not think that only applying global optimization methods will be an ef cient solution to the crystal-structure prediction problem, even with the future exascale HPC facilities. We instead envisage a multistep approach in which high-throughput screening will be the rst stage of the search for stable structure types. The predictions from this rst step will then be re ned by global optimization algorithms, for instance including the structures obtained from HT screening in the initial population of an evolutionary algorithm search or by applying the random mutation operators that in AIRSS are used to explore new parts of the Born-Oppenheimer surface.

In conclusion, the failure of standard high-throughput methods to predict the correct crystal structure of RbCuS and RbCuSe that we illustrate in the present study, leads us to propose a multistep approach to predict new materials. First, perform a high-throughput screening of a set of structure types followed by a global optimization search, for instance using an evolutionary algorithm or random search. This further step will allow to the survey parts of the Born-Oppenheimer surface that would not be otherwise explored by only following the structural analogies with known materials on which the high-throughput methods are based.

ACKNOWLEDGMENTS

The work of M.J.D.V. and K.R.P. was supported in part by the U.S. Department of Energy, Basic Energy Sciences, Of ce of Science, under Contract No. DE-AC02-06CH11357. The work of X.Z. and A.Z. was supported by the Of ce of Science, Basic Energy Science, MSE Division under Grant No. DE-FG02-13ER46959. G.T. used, in this research, resources of the National Energy Research Scienti c Computing Center (NERSC), a U.S. Department of Energy Of ce of Science User Facility, supported by the Of ce of Science of the U.S. Department of Energy under Contract No. DE-AC02-05CH11231. An award of computer time was provided by the ALCC program. As part of this ALCC award, this research used resources of the Argonne Leadership Computing Facility, which is a U.S. Department of Energy Of ce of Science User Facility supported under Contract No. DE-AC02-06CH11357. Single-crystal x-ray data were collected at Northwestern University's Integrated Molecular Structure Education and Research Center (IMSERC) at Northwestern University, which is supported by grants from NSF-NSEC, NSF-MRSEC, the KECK Foundation, the State of Illinois, and Northwestern University.

[1] X. Zhang, L. Yu, A. Zakutayev, and A. Zunger, Adv. Funct. Mater. 22, 1425 (2012).
[2] X. Zhang, V. Stevanovi2222

[27] H. Boller, J. Alloys Compd. 442, 3 (2007).
[28] D. Sheppard, P. Xiao, W. Chemelewski, D. D. Johnson, and G. Henkelman, J. Chem. Phys. 136, 074103 (2012).
[29] D. Wales, Energy Landscapes: Applications to Clusters, Biomolecules and Glasses (Cambridge University Press, Cambridge, 2004).
[30] D. J. Wales, J. Chem. Phys. 142, 130901 (2015).
[31] A. R. Oganov and C. W. Glass, J. Chem. Phys. 124, 244704 (2006).
[32] A. R. Oganov, C. W. Glass, and S. Ono, Earth Planet. Sci. Lett. 241, 95 (2006).
[33] N. L. Abraham and M. I. J. Probert, (2012).